

2K Aerosol

Technical Data Sheet (TDS)

Product Description

Endura 2K Aerosol contains Endura two component coatings packaged in easy-to-use aerosol can.

Product Features:

- Twice the volume solids of conventional aerosol products
- Professional spray gun quality results
- Easy to use
- No mess or measuring
- Quick activation
- No equipment needed

Recommended Uses

All 2K Aerosol products are intended for industrial applications, either new build or maintenance. The 2K Aerosols are convenient for repairs or painting smaller projects.

Read the Technical Data Sheet for the specific paint being sprayed for additional information regarding the product suitability and surface preparation for the project.

Product Characteristics

The product characteristics and dry times of the products can be obtained on the product specific Technical Data Sheets.

Pot Life: Activated (77°F (25°C) and 50% RH)	24 Hours
Shelf Life:	
2K Aerosol	1 years (unactivated)
For unopened product (77°F (25°C))	

2K Aerosol Products Available

2K Aerosols are currently available in the following products:

- EX-2C Topcoat
- EX-2C TF2K Topcoat
- EX-2C SFC Topcoat
- Delta Sealer

Activating 2K Aerosols



1. Shake can vigorously for 2 minutes (after mixing ball rattles) minimum before activating.



2. To Activate, take red button from cap, and attach it to the pin on the aerosol bottom. Put aerosol with cap upside down on a stable surface.



3. Press red button with the ball of your hand until stop is reached.



4. Shake aerosol again vigorously for 2 minutes more to mix paint with hardener.

Application

Once the product is properly activated and shaken, perform a testspray to check the nozzle flow, substrate compatibility and color correctness. The spray fan can be adjusted for vertical or horizontal spray by turning the yellow nozzle orifice. The optimal spraying distance is 8-10inches from the surface being painted.

To prevent the nozzle from clogging, turn the can upside down and push the spray nozzle until only propellant is being sprayed (approximately 2 seconds) between uses.

Ordering Information (sizing)

330g Aerosol	
Product code will vary depending on product	F2KXXXXX-100

Environmental Conditions

For optimum coating performance product, substrate and ambient temperature should be between 68°F-77°F (20°C-25°C). To prevent condensation during application the surface temperature must be 5°F (3°C) or more above the dew point at all times.

For use outside this range please contact your Endura Representative.

Disposal

Dispose of contents in accordance with local, state, provincial and federal regulations

Safety Precautions

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be found on our website at www.endurapaint.com.