

2K Aerosol

Technical Data Sheet (TDS)

Product Description

Endura 2K Aerosol contains Endura two component coatings packaged in easy to use aerosol can.

Product features:

- Twice the volume solids of conventional aerosol products
- Professional spray gun quality results
- Easy to use
- No mess or measuring
- Quick activation
- No equipment needed

Recommended Uses

The 2K Aerosol is excellent for repairs, or for painting smaller projects.

Please read the Technical Data Sheet for the specific product being sprayed for additional important suitability and surface preparation information.

Product Characteristics

The product characteristics and dry times between products can be obtained on the specific product Technical Data Sheets.

2K Aerosol Characteristics:

Pot Life: Once activated the 2K Aerosol can be used for up 24 hours at 68-77°F (20-25°C).

Shelf Life: 1 year for un-activated product.

Endura 2K Aerosol products

2K Aerosols (16oz) are currently available in the following products:

- EX-2C Topcoat
- EX-2C TF2K Topcoat
- EX-2C SFC Topcoat
- Delta Primer

Activating 2K Aerosol Spray Can



1. Shake can vigorously for 2 minutes (after mixing ball rattles) minimum before activating.
2. To Activate, take red button from cap, and attach it to the pin on the aerosol bottom. Put aerosol with cap upside down on a stable surface.
3. Press red button with the ball of your hand until stop is reached.
4. Shake aerosol again vigorously for 2 minutes more to mix paint with hardener.

2K Aerosol Application Method

Once the product is activated, perform a test spray to check nozzle flow, substrate compatibility and color correctness. The spray fan can be adjusted for vertical or horizontal spray by turning the yellow nozzle orifice. Spraying distance is 8-10 inches from the surface being painted.

To prevent the nozzle from clogging, turn can upside down and spray nozzle until only propellant is being sprayed (approx. 2 seconds) between uses.

Clean Up

The emptied aerosols are suitable for household collection.

Environmental Conditions

For optimum coating performance product, substrate and ambient temperature should be between 68°F-77°F (20°C-25°C). To prevent condensation during application the surface temperature must be 5°F (3°C) or more above the dew point at all times.

For use outside this range please contact your Endura Representative.

Safety Precautions

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be found on our website at www.endurapaint.com.