

## EX-FX 85 Anti-Skid HiBuild

### Technical Data Sheet (TDS)

#### Product Description

Endura EX-FX 85 Anti-Skid HiBuild is a two-component HiBuild Epoxy Anti-Skid product designed to provide surface slip resistance.

#### Product features:

- Very Aggressive non-slip surface
- High build
- Easy to use

#### Recommended Uses

EX-FX 85 Anti-Skid HiBuild is intended for industrial applications; either new build or maintenance.

EX-FX 85 Anti-Skid HiBuild is suitable for application on steel, aluminum, fiberglass, and other ferrous metals and concrete.

This primer must be topcoated to achieve the best results.

#### Industries:

- Oilfield & Energy Services
  - Decks & Walkways
- Cranes and Construction Equipment
  - Decks & Walkways
- Waste and Recycling Industry
  - Garbage Trucks
- Concrete floors

#### Mix Ratio

4 parts by volume of Component A [FEA1274]  
1 part by volume of Component B [FEB0275]

The recommended temperature when mixed is 20-25°C (68-77°F).

**Note:** Thinning will manipulate and affect the desired surface finish.

#### Product Characteristics

**Finish:** Aggressive anti-skid (rough texture).

**Volume Solids Mixed:** 76% +/- 1%.

**Pot Life:** 1 Hour at 77°F (25°C) and 50% RH

**VOC Mixed (Unreduced)** (EPA Method 24):  
Warm Grey: 204 g/l (1.703lbs/gallon)

**Shelf Life:** Component A: 3 years at 77°F (25°C)  
Component B: 2 years at 77°F (25°C)

**Note:** For unopened product.

#### Surface Prep

All surfaces must be free of all contaminants such as dust, oil, grease and salt.

**Steel:** It is recommended that all steel and other ferrous surfaces be sandblasted to a minimum of SSPC-SP6 or mechanically sanded with 40 grit sand paper.

**Concrete:** Concrete surface must be properly prepared. Bead blasting, abrasive blasting or acid etching is recommended. (If acid etching the surface it must be left to dry to ensure it is free from any residual moisture).

**New concrete surfaces need to cure for 30 days prior to the application of any coatings.**

#### Aluminum:

**Thin Wall:** Prepare Aluminum surfaces with MetaLink. Read the MetaLink Technical Data Sheet for complete application instructions.

**Note:** Do not use Wax and Grease Remover to clean the surface.

**Thick Wall** It is recommended that all thick wall aluminum surfaces be sandblasted a minimum of SSPC-SP6 or mechanically sanded with 40 grit sand paper.

## EX-FX 85 Anti-Skid HiBuild

### Technical Data Sheet (TDS)

#### Application Method

EX-FX 85 Anti-Skid HiBuild can be rolled using a Goop Loop Roller or sprayed with a hopper gun depending on desired surface finish.

Using the supplied Endura Goop Loop roller sleeve, load the roller sleeve from the paint tray and apply a uniform coat to the surface.

**Note: Do not puddle the product from the mixing pail and roll. Uniformity is difficult to achieve using this method.**

**Note: For small areas too narrow for the roller EX-FX 85 Anti-Skid HiBuild, a pure bristle brush can be used to brush and/or tap the product required.**

Remove all masking tape as soon as the EX-FX 85 Anti-Skid HiBuild is dry beyond tacky. If allowed to dry too long the masking tape will be difficult to remove.

#### Film Build

Endura EX-FX 85 has a minimum recommended film build thickness.

**Dry: 40.0 mils DFT (1000 microns)**

The total Dry Film Thickness may be higher subject to desired finish and performance needs.

Theoretical coverage at 1.0 mil (25 microns)

**Average DFT: 1229 ft<sup>2</sup> per gallon at 100% transfer efficiency.**

**Coverage of EX-FX 85 is approximately 30 sq. ft. per gallon at 40 mils DFT.**

#### Dry Times

	68°F (20°C)
<b>Dry for Foot Traffic</b>	6 -12 hours
<b>Dry for heavy traffic</b>	48 - 72 Hours

**Note: Dry Times are subject to ambient conditions (temperature and humidity) and good airflow and film build of the topcoat.**

For best results surface temperature must be 86°F (30°C) or less before topcoating.

**Note: For questions about scheduling please contact your Endura Representative.**

#### Clean Up

Clean all equipment immediately after use with Endura high strength gun wash, Endura epoxy reducer or Endura EX-2C thinner.

Follow manufacturer's safety recommendations when using any solvent.

#### Ordering Information (sizing)

Available in Gallons.  
Other custom sizes may be available.

5 Quarts		
Comp A – Warm Grey	FEA0274-030	1Gal
Comp B	FEB0275-020	1Qt

#### Environmental Conditions

For optimum coating performance product, substrate and ambient temperature should be between 68°F-77°F (20°C-25°C). To prevent condensation during application the surface temperature must be 5°F (3°C) or more above the dew point at all times.

**Note: For use outside this range please contact your Endura Representative.**

#### Safety Precautions

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be found on our website at [www.endura.ca](http://www.endura.ca).