

## Intermix 2:1 Primer

### Technical Data Sheet (TDS)

#### Product Description

**Intermix 2:1 Primer** is a medium solid, low to medium build, two-component, epoxy primer providing excellent adhesion, hardness and corrosion resistance.

#### Product features:

- No induction time required
- Can be topcoated in 1 hour
- 7 day topcoat window
- Available in various colors

#### Recommended Uses

Intermix 2:1 Primer is intended for industrial applications; either new build or maintenance. Intermix 2:1 Primer is suitable for application on steel, aluminum and fiberglass substrates. This primer must be topcoated to achieve the best results.

**Intermix 2:1 is not recommended in thin films as a sealer.**

#### Industries:

- Oilfield & Energy Services
  - Well Service vehicles
- Cranes and Construction Equipment
- Trailers
- Waste and Recycling Industry
  - Garbage Trucks

#### Mix Ratio

2 parts by volume of component A **[FEAXXXX]**  
[Part Number varies with color]  
1 part by volume of component B **[FEB0179]**

The recommended temperature when mixed is 68-77°F (20-25°C).

#### Product Characteristics

<b>Finish:</b>	Lo Gloss
<b>Volume Solids Mixed: (Unreduced)</b> <b>FEA0170: FEB0179 (2:1)</b>	46% ± 2%
Volume solids will vary by color	
<b>Pot Life:</b> (77°F (25°C) and 50% RH)	10 Hours
<b>VOC Mixed (Unreduced):</b> EPA Method 24 <b>FEA0170:FEB0179 (2:1)</b>	473 g/l 3.948 lb /gal
VOC content will vary with each color	
<b>Shelf Life:</b>	
<b>Component A</b>	3 years
<b>Component B</b>	2 years
<b>For unopened product (77°F (25°C))</b>	

#### Surface Prep

Surface must be free of all contaminants such as dust, oil, grease and salt. It is recommended that all steel and other ferrous surfaces be cleaned to a minimum of SSPC- SP6 or mechanically sanded with 80 grit sandpaper.

For all other substrates refer to the Endura recommended surface preparation instruction sheets or contact your Endura Representative.

#### Application Method

Intermix 2:1 Primer can be applied using most spray painting systems.

Apply 1-2 coats as required to achieve the desired film thickness. Allow sufficient flash time between coats especially with higher film builds applied (20-30 minutes).


## Intermix 2:1 Primer

### Technical Data Sheet (TDS)

#### Spray Gun Setup

Feed Type	Fluid Tip	Application Pressures (heel of gun)	Fluid Delivery
Siphon Feed	1.6-1.8 mm	40-50 psi	
Gravity Feed	1.6-1.8 mm	30-40 psi	
Pressure Feed	1.4-1.8 mm	50-60 psi	10-14 oz/min
Air Assist Airless	9-15 Thou	1,000-1,800 psi	
Airless	9-13 Thou	1,700-3,000 psi	

#### Spray Viscosity



**Note: Spraying viscosity and thinning will depend on ambient conditions, spray equipment used, and the desired surface finish.**

If required, recommended spraying viscosity is achieved by reducing with one of the following Endura Epoxy reducers.

- [FTH0654] Epoxy Reducer - Fast (for use in lower ambient temps)
- [FTH0653] Epoxy Reducer - Regular (for use in average temps)
- [FTH0652] Epoxy Reducer - Slow (for use in higher ambient temps)

#### Film Build

Intermix 2:1 Primer has a recommended film build thickness of:

<b>Wet: WFT Unreduced</b>	<b>4.5 – 8.5 mils</b>	<b>114 – 216 microns</b>
<b>Dry: DFT</b>	<b>2.0 – 4.0 mils</b>	<b>51 – 102 microns</b>

**Note: The recommended dry film thickness is above the blast/sanding profile.**

Theoretical coverage at 1.0 mil (25 microns).  
DFT: 731 ft<sup>2</sup> per gallon at 100% transfer efficiency.

#### Dry Times

	68°F (20°C)	86°F (30°C)	104°F (40°C)
<b>Topcoat</b>	1 Hour	55 Minutes	45 Minutes
<b>Full Cure</b>	7-9 Days	5-6 Days	3-4 Days

**Note: Dry Times are subject to ambient conditions (temperature and humidity) and good airflow and film build of primer.**

For best results, surface temperature must be 86°F (30°C) or less before topcoating.  
Maximum re-coat window without sanding is 7 days at 68°F (20°C)  
Recommended 180 – 220 grit mechanical sanding before topcoating.

**Note: Intermix 2:1 Primer is difficult to sand. If extensive sanding is required we recommend EP Sandable Primer.**

**Note: If the primer is allowed to sit for an extended period without being topcoated, the surface must be kept clean of contaminants to avoid any topcoat issues.**

**For improved scheduling please contact your Endura Representative.**

## Intermix 2:1 Primer

### Technical Data Sheet (TDS)

#### Topcoating Information

Intermix 2:1 Primer can be topcoated with the entire range of Endura topcoat products.

#### Clean Up

Clean all equipment immediately after use with Endura High Strength Gun Wash, Endura epoxy reducer or Endura EX-2C thinner. Follow manufacturer's safety recommendations when using any solvent.

#### Ordering Information (sizing)

Available in Gallons and Pails.  
Other custom sizes may be available.

1.5 Mixed Gallons		
Comp A - Grey	FEA0170-030	1 Gal.
Comp A - Black	FEA0171-030	1 Gal.
Comp A - White	FEA0204-030	1 Gal.
Comp B - 2X	FEB0179-020	1 Qt.

4.5 Mixed Gallons		
Comp A - Grey	FEA0170-053	3 Gals.
Comp A - Black	FEA0171-053	3 Gals.
Comp A - White	FEA0204-053	3 Gals.
Comp B - 1X Plus	FEB0179-030	1 Gal.
Comp B - 2X	FEB0179-020	1 Qt.

#### Environmental Conditions

For optimum coating performance, the product, substrate and ambient temperature should be between 68°F-77°F (20°C-25°C). To prevent condensation during application the surface temperature must be 5°F (3°C) or more above the dew point at all times.

**Note: For use outside this range please contact your Endura Representative.**

#### Specifications

Solvent Resistance	ASTM D4752	100 MEK Rubs; NO Failure
Impact resistance	ASTM D2794	30 in. lbs; NO Failure
Flexibility	ASTM D522	1/4 in. mandrel bend: NO failure
Service Temp Range	-40°F to 250°F	-40°C to 121°C

#### Safety Precautions

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be found on our website at [www.endurapaint.com](http://www.endurapaint.com).