

Technical Data Sheet (TDS)

Dry Time

	68°F (20°C)	86°F (30°C)	104°F (40°C)
To Topcoat	60 mins	30 mins	15 mins

Note: Dry Times are subject to ambient conditions (temperature and humidity) and good airflow and film build of primer.

For best results surface temperature must be 86°F (30°C) or less before topcoating.

Maximum re-coat window without reapplication is 24hrs at 68°F (20°C).

Ordering Information (sizing)

Available in Quarts, Gallons and 5 Gal Pails
Other custom sizes may be available.

Quarts	
P-Link	FAD0013-020

Gallons	
P-Link	FAD0013-030

5 Gal Pails	
P-Link	FAD0013-050

Environmental Conditions

For optimum coating performance product, substrate and ambient temperature should be between 68°F-77°F (20°C-25°C). To prevent condensation during application the surface temperature must be 5°F (3°C) or more above the dew point at all times.

Note: For use outside this range please contact your Endura Representative.

Safety Precautions

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be found on our website at www.endura.ca.