

Super Catalyst II

Technical Data Sheet (TDS)

Product Description

Super Catalyst II is a powerful catalyst for accelerating the curing rate of Endura polyurethane Topcoats. Super Catalyst II accelerates the cure rate of Endura polyurethane topcoats by accelerating the reaction of Component "B" with polyurethane topcoat Component "A".

Product features:

- Accelerates curing time for stripe application
- Improves cool temperature curing
- Will not dramatically reduce pot life of product

Recommended Uses

Super Catalyst II is suitable for use in the following Endura Topcoats.

- EX-2C Topcoat
- EX-2C Low VOC Topcoat
- EX-2C Topcoat Concrete
- EX-2C Topcoat T2FK
- EX-2C Clear 100
- EX-2C Clear 221
- Clarity Clear
- Excel D2M & D2M HS
- G90 Low VOC
- Ultraflex Topcoat
- Kappa Clear Fast & Slow
- Polyglass Edge
-

Note: Super Catalyst II is not intended for use with any other products.

Product Characteristics

Specific Gravity: (77°F (25°C) and 50% RH)	0.983
Shelf Life:	
Super Catalyst I	1 year
For unopened product (77°F (25°C))	

Note: Super Catalyst II will not reduce the pot life significantly of catalyzed products. This is an important consideration when mixing large quantities.

Mixing Ratio

The following mixing ratio applies to all of the Endura polyurethane topcoats listed:

Recommended:

Super Catalyst II: ¼ fluid oz. (7.5 mL)

INTO

Endura Topcoat: 1 mixed US Quart (0.95 L)

Maximum:

Super Catalyst II: 1 fluid oz. (30 mL)

INTO

Endura Topcoat: 1 mixed US Quart (0.95 L)

Note: Super Catalyst II must be added in the recommended ratios to the mixed product only.

Excessive or improper use of Super Catalyst II will cause coating issues including, but not limited to:

- Reduced gloss due to solvent entrapment
- Shorter pot life
- Orange peel finish

Dry Times

The use of Super Catalyst II will shorten the topcoat re-coat window. **It does not increase the speed of solvent release.**

Note: The recoat window is subject to ambient conditions (temperature and humidity) and good airflow and film build of the topcoat.

Note: For Topcoat–Clear Coat application, use Super Catalyst II in the Topcoat color only, or at half the recommended mix ratio amount in the clear coat.

Super Catalyst II should not be used during hot and/or humid conditions.

Super Catalyst II

Technical Data Sheet (TDS)

Ordering Information (sizing)

Available in Pints

Other custom sizes may be available.

1 Pint	
Super Catalyst II	ITB0800-010

Safety Precautions

Please refer to all Safety Data Sheets (SDS) before using this product. SDS sheets can be found on our website at www.endurapaint.com.