

Special B [Rolling Instructions]

Instructions for rolling Endura EX-2C Coating with Ex-2C special B.



Mixing Ratio

EX-2C Special B

2 parts by volume of component A
1 part by volume of component B [FUB0101]



Application Instructions

DO NOT apply when the surface is less than 3°C (5°F) above the dew point.

Pour 1 liter of mixed topcoat onto the floor and roll it out to the desired coverage (Between 50-100ft²)

Application Equipment

Use a short (1/8") pile roller. For areas over 1000ft² use a squeegee to spread out the urethane coatings then back roll with the short pile roller.

Rolling and Tipping

Brush/Roller application:

Ensure that the surface is free of flaws, nibs or imperfections. If large imperfections exist after primer coat use 120-150 grit sandpaper to remove them. Use a vacuum cleaner to remove all dust from the surface.

On large surfaces first roll the Endura Topcoat and then smooth the roller stipple by lightly tipping the surface with a brush. This can be done with 2 painters working side by side (i.e., 1 rolling and 1 tipping), or with 1 painter rolling approximately 6 square feet and then tipping that area before rolling any further.

Notes

Please see Endura EX-2C datasheet for full usage instructions.