

Technical Bulletin #70 Issue Date: September 14, 2020

EX-2C Clear 116 MG,117 LG,118 NG

This technical notice is regarding the preparation of the EX-2C Clear 116 MG,117 LG,118 NG after 24 hours cure.

These reduced gloss clears provide a harder and slicker surface than the standard EX-2C Clear 100.

If these clears need to be recoated, they must be sanded with 180-240 grit sandpaper for good intercoat adhesion. Using a maroon nylon scuff pad will NOT provide enough surface abrasion for good intercoat adhesion.

For any questions please call your Endura Paint Representative at 1-800-661-9930.