

**Technical Bulletin #24****Oct 28, 2003****EX-2C Clear 100 and EX-2C Mid-coat Clear**

Endura EX-2C Clear 100 has additives that give it great mar and scratch resistance. When Endura EX-2C Clear 100 is recoated after 18-24 hours (not wet on wet) regardless of sanding there is the possibility of cratering and fish-eyes occurring. Endura recommends the option, of using the product EX-2C Mid-coat Clear, before the EX-2C Clear 100 for the final coat. Endura Manufacturing Co. Ltd. Developed the EX-2C Mid-coat Clear without the mar resistant additives to lend it to better recoatability but does not have the durability of EX-2C Clear 100. For this reason, Endura recommends the use of EX-2C Clear 100 for the final coat.

Endura Lab Staff